



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> : C03C 17/38, G02B 5/08	A1	(11) International Publication Number: WO 99/47465 (43) International Publication Date: 23 September 1999 (23.09.99)
--	----	---

(21) International Application Number: PCT/US99/05491

(22) International Filing Date: 12 March 1999 (12.03.99)

(30) Priority Data:  
60/078,138 16 March 1998 (16.03.98) US

(71) Applicant: MASSACHUSETTS INSTITUTE OF TECHNOLOGY [US/US]; 77 Massachusetts Avenue, Cambridge, MA 02139 (US).


(72) Inventors: FINK, Yoel; Apartment 22E, 60 Wadsworth Street, Cambridge, MA 02142 (US); THOMAS, Edwin, L.; 14 Apple Ridge Drive, Natick, MA 01701 (US). WINN, Joshua; 16 Josephine Avenue #2, Somerville, MA 02144 (US). FAN, Shanhui; 50 Porter Street, Somerville, MA 02143 (US). CHEN, Chiping; 125 Brookline Street, Needham, MA 02192 (US). JOANNOPOULOS, John, D.; 64 Douglas Road, Belmont, MA 02178 (US).

(74) Agents: CONNORS, Matthew, E. et al.; Samuels, Gauthier &amp; Stevens, Suite 3300, 225 Franklin Street, Boston, MA 02110 (US).

(81) Designated States: CA, JP, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).

**Published***With international search report.**Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.*

(54) Title: POLYMER-INORGANIC MULTILAYER DIELECTRIC FILM



## (57) Abstract

A multilayer dielectric film structure includes a pair or plurality of materials at least one being a polymer and the other of high index of refraction inorganic material (compared to the polymer) at the wavelengths of interest. The structure is fabricated by a combination of layering techniques, one of which is used to create a layer of the polymer, the other being used to deposit the inorganic component. The assembly process yields a structure of alternating polymer and inorganic layers of high index of refraction (compared to air). The structure preferably will reflect light within a certain frequency range of any polarization and at a continuum of angles of incidence ranging from normal to oblique. In a particular embodiment of the invention, the structure includes alternating layers of a polymer, e.g., polystyrene and Tellurium.

*FOR THE PURPOSES OF INFORMATION ONLY*

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Larvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

- 1 -

## POLYMER-INORGANIC MULTILAYER DIELECTRIC FILM

### BACKGROUND OF THE INVENTION

The invention relates to the field of multilayer dielectric film structures, and in particular to structures with high reflectivity characteristics.

Multilayer dielectric films are used in a wide variety of optical devices which typically utilize the frequency selective reflectivity that these films exhibit. Most of the current applications involve the reflection or transmission of light of nearly normal incidence, although grazing angle applications exist as well. The optical response of a multilayer dielectric film to light of off-normal incidence has been investigated, and is angle-of-incidence and polarization dependent.

If properly constructed, a multilayer dielectric film will have selective frequency regions of high and low reflectivity. In general, the bandwidth of the high reflectivity region shrinks for one of the polarizations (transverse magnetic (TM), E vector in the plane of incidence) and increases for the other (transverse electric (TE), E vector transverse to the plane of incidence) as the angles of incidence become more oblique. In fact, the width of the reflective region shrinks to zero for the TM mode at the Brewster angle. Methods for reducing the angular dependence of the width of the reflective region are known and include the use of high index of refraction materials as layer components.

20

### SUMMARY OF THE INVENTION

The materials system or multilayer dielectric film structure of the invention includes of a pair or plurality of materials at least one being a polymer and the other of high index of refraction inorganic material (compared to the polymer) at the wavelengths of interest.

The structure is fabricated by a combination of layering techniques, one of which is used to create a layer of the polymer, the other being used to deposit the inorganic component.

The assembly process yields a structure of alternating polymer and inorganic layers of high index of refraction (compared to air). The structure preferably will reflect light within a certain frequency range of any polarization and at a continuum of angles of incidence ranging from normal to oblique. In a particular embodiment of the invention, the structure

30

- 2 -

### **BRIEF DESCRIPTION OF THE DRAWINGS**

FIG. 1 is a simplified block diagram of an exemplary embodiment of a multilayer dielectric film structure in accordance with the invention;

5        FIG. 2 is a simplified block diagram of an exemplary embodiment of a multilayer dielectric film structure including alternating layers of a polystyrene polymer and tellurium in accordance with the invention; and

FIG. 3 are plots of measured (dashed) and calculated (solid) reflectance vs. wavelength for nine layer tellurium polystyrene multilayer film for the two polarizations TE  
10 and TM, and for light of  $0^\circ$ ,  $45^\circ$  and  $80^\circ$  of incidence showing a high reflectivity region from 10-15 microns.

### **DETAILED DESCRIPTION OF THE INVENTION**

The materials system of the invention consists of one or more polymers or blends  
15 thereof, such as polyethylene, polystyrene, polyvinilidene flouride, polyvinylpyrillidone, poly methylene (polyphenyl isocyanate) and a compatible high index of refraction component, such as tellurium, germanium and cadmium selenide (CdSe). FIG. 1 is a simplified block diagram of an exemplary embodiment of a multilayer dielectric film structure 100 in accordance with the invention. The structure 100 includes alternating  
20 layers of a first material 102 of a polymer or blend with an index of refraction  $n_2$  and thickness  $h_2$  and a second material 104 of a compatible high index refraction component  $n_1$  and thickness  $h_1$  on a substrate 106. Also in FIG. 1 are the incident wave vector  $k$  originating from the ambient medium  $n_0$  and the electromagnetic mode convention TM and TE.

25        In applications involving the use of the structure 100 for reflecting purposes, it will be appreciated that all of the individual film materials used have some degree of transparency for the wavelength range of interest. The compatibility of the materials are taken in the broadest sense subject to the proximity imposed by the structure and the particular method of assembly. For example, a polymer with traces of acetone will damage  
30 a tellurium layer. The polymers chosen will also preferably have a low degree of crystallinity and low diffusivity for the complementary component of the second material.

- 3 -

The two (or more) components will also have chemical compatibility, i.e., the materials will not degrade when in contact with one another, physical compatibility, i.e., the materials will be able to form a well defined intimate interface, and have low interdiffusivity constants at process temperatures. For example, tellurium has a high diffusion rate in low molecular weight polyethylene at temperatures existing in a vacuum evaporation process.

The layers can be assembled on a substrate and subsequently removed or coated directly onto a surface that is part of the application. The surface should be wetted by the material that forms the first layer. The substrate can be treated with a surface modifying group for good adherence or easy removal of the assembled structure. An exemplary assembly of layers which can be subsequently removed includes a glass surface coated initially with Victawet, a sodium salt of 2-ethylhexyl acid phosphate provided by SPI Inc., and then sequentially layered with the selected materials. After assembly, the dielectric multilayer film can be removed from the Victawet coated glass substrate by using water, which will not damage a hydrophobic polymer.

Polymer layers of controlled thickness can be deposited by a variety of known techniques, for example, by spin coating a polymer layer from a solvent using a spin coating apparatus. The concentration of the solution and the spin speed can be used to control thickness. Evaporation casting can be also used to deposit polymer layers. In this technique a dilute solution of the polymer is prepared, which is then cast on the surface. The solvent subsequently evaporates and a thin film of polymer is formed.

A layer can also be formed by polymerizing a monomer in-situ, for example, styrene (65% volume), divinylbenzene (34% volume) and benzoyl peroxide (~1%) can be combined and irradiated with UV to form a heavily crosslinked polystyrene network on the surface.

A polymer layer can also be deposited by heat or vacuum evaporation or by spraying onto a surface. In the assembly process, care should be taken to prevent damage of underlying layers by the presence of solvent, in general a technique which involves a minimal presence of solvent such as spin coating is preferable.

The optical response of a particular dielectric multilayer film can be predicted using the characteristic matrix method as described in Driscoll et al., *Handbook of Optics*, McGraw-Hill, 8-42 – 8-43 (1978), incorporated herein by reference. In this method, a 2x2 unitary matrix is constructed for each layer of the structure. This matrix represents a

- 4 -

predict the optical response of a multilayer film, the characteristic matrix for each layer needs to be calculated. The form of the characteristic matrix for the  $j^{\text{th}}$  layer is

$$m^g(\theta)_j = \begin{bmatrix} \cos\beta_j & -\frac{i}{p^g_j} \sin\beta_j \\ -ip^g_j \sin\beta_j & \cos\beta_j \end{bmatrix} \quad (g = \text{TE, TM})$$

5

$$\beta_j = kh_j \sqrt{n_j^2 - \text{snell}(\theta)^2}$$

$$\text{snell}(\theta) = n_0 \sin\theta_0$$

$$p^g_j = \begin{cases} \sqrt{n_j^2 - \text{snell}(\theta)^2} & g = \text{TE} \\ \frac{\sqrt{n_j^2 - \text{snell}(\theta)^2}}{n_j^2} & g = \text{TM} \end{cases}$$

where  $n_j$  is the index of refraction,  $h_j$  is the thickness of the  $j^{\text{th}}$  layer,  $\theta_0$  is the angle between the incident wave and the normal to the surface, and  $n_0$  is the index of the initial  
10 medium (e.g. air).

The matrices are then multiplied to give the film's characteristic matrix

$$M^g(\theta) = \prod_{j=1}^N m^g_j \quad (g = \text{TM or TE})$$

which in turn can be used to calculate the reflectivity for a given polarization and angle of  
15 incidence,

$$R^g(\theta) = \frac{\left| (M_{11}^g(\theta) + M_{12}^g(\theta)p^{g_1})p^{g_0} - (M_{21}^g(\theta) + M_{22}^g(\theta)p^{g_1}) \right|^2}{\left| (M_{11}^g(\theta) + M_{12}^g(\theta)p^{g_1})p^{g_0} + (M_{21}^g(\theta) + M_{22}^g(\theta)p^{g_1}) \right|^2}$$

where  $p^{g_0}$  contains information about the index of the medium and angle of incidence on one side of the multilayer film and  $p^{g_1}$  contains information about the index of the medium  
20 and angle of incidence on the other.

In certain embodiments, a finite periodic film consisting of alternating layers of materials with different indices of refraction is formed which exhibits high reflectivity for a particular range of frequencies determined by the respective thickness of the layers and

- 5 -

their indices of refraction. The center frequency of the high reflectivity region at a particular angle of incidence  $\theta$  is given by

$$\omega_{\text{midgap}}^g(\theta) = \frac{c}{h_2 \sqrt{n_2^2 - \text{snell}^2(\theta)} + h_3 \sqrt{n_3^2 - \text{snell}^2(\theta)}} \left\{ \cos^{-1} \left( - \sqrt{\frac{\Lambda^g(\theta) - 1}{1 + \Lambda^g(\theta)}} \right) + \cos^{-1} \left( + \sqrt{\frac{\Lambda^g(\theta) - 1}{1 + \Lambda^g(\theta)}} \right) \right\}$$

5

The extent in frequency of this region for a given angle of incidence  $\theta$  and at a particular polarization  $g$  is given by

$$\Delta\omega^g(\theta) = \frac{2c}{h_2 \sqrt{n_2^2 - \text{snell}^2(\theta)} + h_3 \sqrt{n_3^2 - \text{snell}^2(\theta)}} \left\{ \cos^{-1} \left( - \sqrt{\frac{\Lambda^g(\theta) - 1}{1 + \Lambda^g(\theta)}} \right) - \cos^{-1} \left( + \sqrt{\frac{\Lambda^g(\theta) - 1}{1 + \Lambda^g(\theta)}} \right) \right\}$$

where

$$10 \quad \Lambda^g(\theta) = \frac{1}{2} \left( \frac{p^g_2}{p^g_3} + \frac{p^g_3}{p^g_2} \right)$$

$n_2$ ,  $n_3$  are the indices of refraction of the two layers repeated throughout the structure,  $h_2$ ,  $h_3$  are their thickness, and  $c$  is the speed of light in vacuum.

FIG. 2 is a simplified block diagram of an exemplary embodiment of a multilayer dielectric film structure 200 in accordance with the invention. The structure 200 includes  
15 alternating layers of a polystyrene (PS) polymer 202 and tellurium (Te) 204. The polymer exhibits low loss in the 2.5-25 micron range, has excellent mechanical properties, and forms continuous ultra smooth films. The index of refraction for the polymer is very close to 1.5 across the entire frequency range of interest.

Tellurium is an element with low infrared (IR) absorption and high index of  
20 refraction in the 2.5-25 micron wavelength region. It is chemically stable, does not oxidize easily, and has low diffusivity in polystyrene. In addition, tellurium adheres well to polymers and forms consistent layers from vacuum evaporation which are environmentally stable. Tellurium films are able to conduct moisture and small solvent molecules, and may be considered a "breathable" material. It has a low latent heat of evaporation ~105kJ/mol  
25 compared with germanium 327kJ/mol and a relatively low boiling point (990°C) which allows for low temperature processing and minimizes heat damage. Another benefit of the small latent heat content is low diffusivities upon condensation since relatively little heat is released. Both the polymer and tellurium are non-carcinogenic and are non-toxic in the

- 6 -

bulk form (i.e., no dust).

The assembly method includes spin coating at 1000RPM onto a NaCl window (Wilmad 25mm). The solution was 10% weight of polystyrene (GoodYear molecular weight=120k) in toluene. An additional evaporation stage at room temperature for 3 hours followed the spin coating to ensure complete solvent removal.

The tellurium (Strem Chemicals broken ingots) was evaporated in a vacuum evaporator (Ladd model 30000) under a  $5 \times 10^{-6}$  Torr vacuum and at a current of 7Amps, which yielded a maximum evaporation rate of 3 angstrom per second. The film thickness and evaporation rate was monitored in-situ using a Crystal Film Thickness Monitor (Sycon Instruments model STM100), and final film thickness was determined with a profilometer (Tencor model P10). The tellurium and polystyrene films were deposited sequentially leading to the formation of a nine layer film as follows: Te/PS/Te/PS/Te/PS/Te/PS/Te.

The optical response of this particular multilayer film was designed to have a high reflectivity region in the 10-15 micron range by choosing the appropriate quarter-wave thicknesses such that  $n_{Te} h_{Te} = n_{PS} h_{PS} = 12.5 / 4$  at angles of incidence ranging from 0 to 80 degrees at least. The optical response was predicted using the method outlined above and measured using a Fourier Transform Infra Red Spectrometer (Nicolet 860) fitted with a polarizer (ZnS SpectraTech) and an angular reflectivity stage (VMAX by SpectraTech).

A comparison of the predicted and measured optical response is presented in the figures below. FIGs. 3 are plots of measured (solid) and calculated (dashed) reflectance vs. wavelength for nine layer tellurium polystyrene multilayer film for the two polarizations TE and TM (d,e,f), and for  $0^\circ$ ,  $45^\circ$  and  $80^\circ$  angles of incidence showing a high reflectivity region from 10-15 microns.

The measured and predicted optical response of the exemplary nine layer tellurium polystyrene film of FIG. 2 is shown in FIG. 3 for normal incidence, and for light incident at  $30^\circ$  for TE and TM modes. Where the electric field is perpendicular to the plane defined by the wave vector and the normal to the surface in the TM mode and in the plane for the TE mode.

A high reflectivity region is predicted and observed for normal incidence light extending from 10-20 microns. The slope of the boundaries enclosing this region can be increased by increasing the number of layers. As the angle of incidence is increased, the



- 7 -

qualitative behavior of the two modes differ. The width of the high reflectivity region for the TE mode increases at increasingly oblique angles of incidence. The width of this same region for the TM mode shrinks, however, for the materials illustrated in the exemplary embodiment does not disappear in fact at 80° incidence, the width is still larger than 3  
5 microns.

In addition to the reflectance due to the stratified structure, absorption is also present. In fact, polymers are known to have distinct absorption bands in the IR corresponding to the excitation of vibrational modes of different bonds. The dip located in the vicinity of 14 microns is an example of a known absorption band for polystyrene  
10 (Aldrich Library of FTIR spectra). It will be appreciated that this absorption peak grows at larger angles of incidence reflecting the increasing path of the light in the polystyrene layer. It is also more pronounced for the TM mode. The total thickness of the exemplary seven layer device is approximately 9 microns.

Although the present invention has been shown and described with respect to  
15 several preferred embodiments thereof, various changes, omissions and additions to the form and detail thereof, may be made therein, without departing from the spirit and scope of the invention.

What is claimed is:

- 8 -

CLAIMS

- 1 1. A multilayer dielectric film structure comprising a plurality of alternating layers of  
2 polymeric material and inorganic material.
- 1 2. The structure of claim 1, wherein said alternating layers are transparent for  
2 predetermined wavelength ranges.
- 1 3. The structure of claim 1, wherein said inorganic material comprises non-metallic  
2 material.
- 1 4. The structure of claim 1, wherein said layers of polymeric material comprise at least  
2 one polymer.
- 1 5. The structure of claim 1, wherein said layers of polymeric material comprise a  
2 varying plurality of polymers.
- 1 6. The structure of claim 1, wherein said layers of polymeric material comprise  
2 polymeric blends.
- 1 7. The structure of claim 1, wherein said layers of said inorganic material comprise at  
2 least one inorganic material.
- 1 8. The structure of claim 1, wherein said layers of said inorganic material comprise a  
2 varying plurality of inorganic materials.
- 1 9. The structure of claim 1, wherein a contrast of index of refraction exists between  
2 each of said alternating layers.
- 1 10. The structure of claim 1, wherein each of said alternating layers comprises at least  
2 one polymeric material layer and inorganic material layer, respectively.

- 9 -

1 11. The structure of claim 1, wherein said polymeric material includes polyethylene,  
2 polystyrene, polyvinilidene fluoride, or polyvinylpyrrolidone.

1 12. The structure of claim 1, wherein said inorganic material includes tellurium,  
2 germanium, or cadmium selenide.

1 13. The structure of claim 1, wherein said polymeric material comprises polystyrene and  
2 said inorganic material comprises tellurium.

1 14. The structure of claim 1, wherein said inorganic material comprises a transparent  
2 metallic inorganic material.

1 15. The structure of claim 1, wherein said structure is highly reflective within a  
2 predetermined frequency range of any polarization and at a continuum of angles of  
3 incidence ranging from normal to oblique.

1 16. The structure of claim 1, wherein said structure comprises a coating.

1 17. A method of fabricating a multilayer dielectric film structure comprising:  
2 providing a surface layer;  
3 depositing a first layer of one of a polymeric material or an inorganic material on  
4 said surface layer;  
5 depositing a second layer of the other of a polymeric material or an inorganic  
6 material on said first layer; and  
7 alternately depositing a subsequent sequence of said first and second layers on said  
8 second layer.

1 18. The method of claim 17, wherein said surface layer comprises a wetted surface.

1 19. The method of claim 17, wherein said surface layer comprises a substrate from  
2 which the sequence of first and second layers are removed.

- 10 -

1 20. The method of claim 17, wherein the alternate sequence of first and second layers  
2 is provided as a coating.

1 21. The method of claim 17, wherein the alternate sequence of said first and second  
2 layers are transparent for predetermined wavelength ranges.

1 22. The method of claim 17, wherein said inorganic material comprises non-metallic  
2 material.

1 23. The method of claim 17, wherein the layers of polymeric material comprise at least  
2 one polymer.

1 24. The method of claim 17, wherein the layers of polymeric material comprise a  
2 varying plurality of polymers.

1 25. The method of claim 17, wherein the layers of polymeric material comprise  
2 polymeric blends.

1 26. The method of claim 17, wherein the layers of said inorganic material comprise at  
2 least one inorganic material.

1 27. The method of claim 17, wherein the layers of said inorganic material comprise a  
2 varying plurality of inorganic materials.

1 28. The method of claim 17, wherein a contrast of index of refraction exists between  
2 each of the alternating layers.

1 29. The method of claim 17, wherein each of the alternating layers comprises at least  
2 one polymeric material layer and inorganic material layer, respectively.

- 11 -

1 30. The method of claim 17, wherein said polymeric material includes polyethylene,  
2 polystyrene, polyvinilidene fluoride, or polyvinylpyrrolidone.

1 31. The method of claim 17, wherein said inorganic material includes tellurium,  
2 germanium, or cadmium selenide.

1 32. The method of claim 17, wherein said polymeric material comprises polystyrene and  
2 said inorganic material comprises tellurium.

1 33. The method of claim 17, wherein said inorganic material comprises a transparent  
2 metallic inorganic material.

1 34. The method of claim 17, wherein said structure is highly reflective within a  
2 predetermined frequency range of any polarization and at a continuum of angles of  
3 incidence ranging from normal to oblique.

1 35. A multilayer dielectric film reflector comprising a plurality of alternating layers of  
2 polymeric material and Tellurium.

1 36. The reflector of claim 35, wherein said polymeric material comprises polystyrene.

1 37. The reflector of claim 35, wherein said layers of polymeric material comprise at least  
2 one polymer.

1 38. The reflector of claim 35, wherein said layers of polymeric material comprise a  
2 varying plurality of polymers.

1 39. The reflector of claim 35, wherein said reflector exhibits high reflectivity  
2 characteristics for a predetermined range of frequencies for incident electromagnetic energy  
3 at a plurality of incident angles and any polarization.

- 12 -

1 40. The reflector of claim 39, wherein said range of frequencies comprises a range from  
2 about 2.5 $\mu$ m to about 25 $\mu$ m.

1 41. The reflector of claim 40, wherein said range of frequencies comprises a range from  
2 about 10 $\mu$ m to about 15 $\mu$ m.

1 42. The reflector of claim 35, wherein the total number (N) of layers, the layer thickness  
2 ( $h_2, h_3$ ) and corresponding indices of refraction ( $n_2, n_3$ ) are determined to provide a  
3 reflectivity  $R^g(\theta)$  of a predetermined value for a particular frequency, polarization g and  
4 angle of incidence  $\theta$  in accordance with

$$5 \quad R^g(\theta) = \frac{\left| (M_{11}^g(\theta) + M_{12}^g(\theta)p^{g_1})p^{g_0} - (M_{21}^g(\theta) + M_{22}^g(\theta)p^{g_1}) \right|^2}{\left| (M_{11}^g(\theta) + M_{12}^g(\theta)p^{g_1})p^{g_0} + (M_{21}^g(\theta) + M_{22}^g(\theta)p^{g_1}) \right|^2}$$

6 where

$$7 \quad M^g(\theta) = \prod_{j=1}^N m^g_j \quad (g = \text{TM or TE})$$

8 and

$$9 \quad m^g(\theta)_j = \begin{bmatrix} \cos\beta_j & -\frac{i}{p_j^g} \sin\beta_j \\ -ip_j^g \sin\beta_j & \cos\beta_j \end{bmatrix} \quad (g = \text{TE, TM})$$

10

$$\beta_j = kh_j \sqrt{n_j^2 - \text{snell}(\theta)^2}$$



$$11 \quad \text{snell}(\theta) = n_0 \sin \theta_0$$






$$p_j^g = \begin{cases} \sqrt{n_j^2 - \text{snell}(\theta)^2} & g = \text{TE} \\ \frac{\sqrt{n_j^2 - \text{snell}(\theta)^2}}{n_j^2} & g = \text{TM} \end{cases}$$

12 where  $n_j$  is the index of refraction,  $h_j$  is the thickness of the  $j^{\text{th}}$  layer,  $\theta_0$  is the angle  
13 between the incident wave and the normal to the surface, and  $n_0$  is the index of the initial  
14 medium.

1 43. The reflector of claim 1, wherein said reflector comprises a coating.

1 / 2

**FIG. 1****FIG. 2**

**FIG.  
3A****FIG.  
3B****FIG.  
3C****FIG.  
3D****FIG.  
3E**



# INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/05491

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C03C17/38 G02B5/08

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 G02B C03C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	US 5 814 367 A (SCHRIER BRUCE H ET AL) 29 September 1998  see column 2, line 30 - line 35 see column 3, line 61 - column 5, line 30 see column 7, line 50 - column 8, line 61 ---	1, 2, 4, 7, 9-21, 23, 26, 28-37, 39, 43
X	WO 92 16875 A (COSTICH VERNE R) 1 October 1992  see page 4, line 21 - page 6, line 34 --- -/--	1-4, 7, 9-12, 14, 16, 35, 37, 39-42

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

1 July 1999

Date of mailing of the international search report

12/07/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Ciarrocca, M

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/05491

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	GB 1 198 904 A (HITACHI LTD) 15 July 1970  see page 3, line 24 - line 40 ----	1,2,4, 9-16, 35-37, 39,43
X A	US 5 071 206 A (HOOD THOMAS G ET AL) 10 December 1991  see column 5, line 9 - column 6, line 21; figure 2 ----	1,2,4,7, 9,10,15, 16 17,35
X	EP 0 733 919 A (CATALINA COATINGS INC) 25 September 1996  see claims 1-6,21-25 ----	1,2,4,7, 9,10,14, 17-19, 21,23, 26,28, 29,33
X	US 4 340 646 A (OHNO AKIRA ET AL) 20 July 1982 see column 11, line 38 - line 64; claims 3-5 ----	1,3,7,8, 10
E	EP 0 913 432 A (NAKATSUKA KATSUTO ;NITTETSU MINING CO LTD (JP)) 6 May 1999 see paragraph 68 - paragraph 73; table 4 & WO 97 47693 A (NITTETSU MINING CO LTD) 18 December 1997 ----	1-4,7, 9-11
X	DATABASE WPI Section Ch, Week 8721 Derwent Publications Ltd., London, GB; Class A23, AN 87-146477 XP002107892 & JP 62 083140 A (TORAY IND INC) , 16 April 1987 see abstract ----	1-4,7-10
A	EP 0 469 732 A (DOW CHEMICAL CO) 5 February 1992 see column 7, line 32 - line 38 ----	6,25
A	PATENT ABSTRACTS OF JAPAN vol. 007, no. 224 (P-227), 5 October 1983 & JP 58 114395 A (FUJITSU KK), 7 July 1983 see abstract -----	1,35

# INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/US 99/05491

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5814367 A	29-09-1998	NONE	
WO 9216875 A	01-10-1992	US 5233464 A DE 69220218 D DE 69220218 T EP 0577732 A US 5426532 A	03-08-1993 10-07-1997 15-01-1998 12-01-1994 20-06-1995
GB 1198904 A	15-07-1970	US 3551017 A	29-12-1970
US 5071206 A	10-12-1991	CA 1335086 A US 4799745 A, B AU 625754 B AU 2939989 A EP 0454666 A WO 9008334 A	04-04-1995 24-01-1989 16-07-1992 13-08-1990 06-11-1991 26-07-1995
EP 0733919 A	25-09-1996	US 5877895 A CA 2172113 A CA 2235948 A JP 8332450 A	02-03-1999 21-09-1996 21-09-1996 17-12-1996
US 4340646 A	20-07-1982	JP 55065547 A JP 58033099 B DE 2945823 A	17-05-1980 18-07-1983 14-05-1980
EP 0913432 A	06-05-1999	JP 9328630 A JP 9328412 A JP 9328674 A AU 3048497 A NO 985793 A CA 2258115 A WO 9747693 A	22-12-1997 22-12-1997 22-12-1997 07-01-1998 10-02-1999 18-12-1997 18-12-1997
EP 0469732 A	05-02-1992	US 5103337 A CA 2047603 A JP 4313704 A US RE34605 E	07-04-1992 25-01-1992 05-11-1992 10-05-1994

THIS PAGE BLANK (USPTO)